

PVDC Coated BOPET Film on both sides (SD-B1T1)

DESCRIPTION:

SD-B1T1 grade is biaxially oriented polyester film coated on both sides with an aqueous dispersion of polyvinylidene designed for flexible packaging applications.

CHARACTERISTICS:

- ◆ Excellent oxygen barrier, outstanding flavor and aroma barrier
- ◆ Excellent heat resistance, the best mechanical strength
- ◆ Outstanding properties of printable
- ◆ Can not be contact with alcohol

TECHNICAL DATA:

TECHNICAL DATA

Properties	Test	Unit	Typical Value	
PHYSICAL				
Thickness	SD Test	Micron(mil)	15(0.59)	
Yield	SD Test	m ² /kg(in ² /lb)	47.17(33164)	
Unit Weight	SD Test	g/m ² (lb/ream)	21.2(13.01)	
OPTICAL				
Haze	ASTM D1003	%	2.5	
Gloss(45℃) Acrylic side	ASTM D2457	%	100	
MECHANICAL				
Tensile strength	MD	ASTM D882	Mpa(Kpsi)	195(28281)
	TD			185(26831)
Elongation at break	MD	ASTM D882	%	90
	TD			100
C.O.F.	ASTM D1894	/	0.35	
THERMAL				
Heat Resistance	MD	ASTM D1204	%	0.5
	TD			0
Seal Strength	ASTM F 88 135℃,0.25MPa,0.5sec		N/15mm(g/in)	1.0(173)
SURFACE				
Surface tension	ASTM D2578	Dynes/cm	42	
BARRIER				
WVTR-38℃,90%RH	ASTM F1249	g/m ² /24h (g/100in ² /24h)	7.0(0.45)	
OTR-23℃,0%RH	ASTM D3985	cm ³ /m ² · 24h (cc/100in ² · 24h)	6.5(0.42)	

Note: The stated values are typical data and are not specification of guarantee. SD Pack suggest that purchaser confirm product compatibility prior to use of this product. Stated values are believed to be accurate, but all information is presented without guarantee or responsibility on the part of SD Pack CO., LTD.



Shanghai Saidian Packing Materials Co., Ltd.

Head Office: No.190 Meihe Road, Qingpu Dist., Shanghai, PRC

Tel: +86 21 51601858 Fax: +86 21 51567115

Web site: [http:// www.sdianpack.com](http://www.sdianpack.com)

E-mail: sales@sdianpack.com